



HD5000S

High Density Polyethylene Resin

Product Description

InnoPlus HD5000S is high density polyethylene resin which offers good balance of processability, high production rates, excellent tenacity and good appearance. InnoPlus HD5000S is recommended for monofilament or yarn applications

Typical Application : Rope, Fishing net, Agricultural net, Tarpaulin, Woven sack

Typical Properties :

| Properties | Value | Unit | Method |
|--|---------|--------------------|------------|
| Physical Properties | | | |
| Melt Flow Rate (2.16 kg/190 °C) | 0.8 | g/10 min | ASTM D1238 |
| Density (21.6 kg/190 °C) | 0.954 | g/cm ³ | ASTM D1505 |
| Vicat Softening Point @ 10 N, 50 °C/hr | 125 | °C | ASTM D1525 |
| Melting Point | 130 | °C | ASTM D2117 |
| Mechanical Properties | | | |
| Tensile Strength @ Yield | 290 | kg/cm ² | ASTM D638 |
| Tensil Strength @ Break | 390 | kg/cm ² | ASTM D638 |
| Elongation @ Break | >1000 | % | ASTM D638 |
| Stiffness | 8500 | kg/cm ² | ASTM D747 |
| Flexural Modulus | 12000 | kg/cm ² | ASTM D790 |
| Notched Izod Impact | 23 (P)* | kg.cm/cm | ASTM D256 |
| Durometer Hardness | 64 | Shore D | ASTM D2240 |
| ESCR (Condition B, 25 % Igepal) | 30 | hrs, F50 | ASTM D1693 |

* P = Partial Break

Recommendation :

Extruder temperature : 200-260 $^\circ\text{C}$ Die temperature : 250-260 $^\circ\text{C}$

Stretching temperature : 97-100 °C Stretching ratio : 8-10

FDA Statement :

HDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 regulation for polyethylene used in articles that contact food except for articles used for packaging or holding food during cooking.

Note : Properties reported here are typical values of the product, not to be considered as specifications. PTT Chemical makes no representations as to the accuracy or completeness of the information contained herein.

PTT Polymer Marketing Company Limited

Energy Complex Building A, 9thFloor, 555/1 Vibhavadi Rangsit Road, Chatuchak, Bangkok 10900 Tel: 66 2140 4487 Fax: 66 2140 4335