

PP

▶ BB310


Block copolymer for sheet application

Description

BB310 is a propylene-ethylene block copolymer designed for sheet application. Clear & Soft characteristics of BB310 lead excellent impact strength/transparency balance.

Characteristics

► High impact strength



Chartry Chartry Program of the Chartry Chartry

<BB310>

<General Random PP>

- ► Low fish-eye level
 - Optical property (500 µm calendering sheet)

	Method (ASTM)	Unit	BB310
Haze	D1003	%	30

^{*} Processing temperature : 230°C,

Data performed by or on behalf of Hanwha Total

Applications

- ► Transparent/Semi-transparent Sheet
- ► Household Case
- Stationery

^{*} Chill-roll temperature : 70° C



Physical Properties

Typical Properties	Method (ASTM)	Unit	BB310
Melt flow index	D1238	g/10min	5.0
Density	D1505	g/cm ³	0.91
Tensile strength at yield	D638	kg/cm ²	275
Elongation at break	D638	%	>600
Flexural modulus	D790	kg/cm ²	10,000
Izod impact strength 23 ℃	D256	kgcm/cm	15
Rockwell hardness	D785	R-scale	63
Heat distortion temp.	D648	$^{\circ}$	103

^{*} Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Food Contact Application

▶ To apply Hanwha Total BB310 to the food packaging, the verification on the suitability is necessary. In case you might need additional regulatory information, please contact Hanwha Total Polymer Technical Service Team.

Contacts

▶ Product Information & Technical Services

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do, Korea, 31900

TEL: 82-41-660-6190 FAX: 82-41-660-6189

Disclaimer

This document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.

^{*} Data performed by or on behalf of Hanwha Total